

EGB DYES



 EQUINATIVE EGB SERIES	Shade 2.0% o.w.f.	Solubility in gpl at 30 °C	Affinity	Reactivity	Fixation Temperature °C	Process Suitability				Dischargeability	Other Fastness		Light Fastness AATCC 16E			Post Fastness Properties			
						Exhaust	Cold Pad Batch	Printing	Continuous		Washing Fastness ISO 105 C04	Rubbing ISO 105/X12 Dry / Wet	0.1%	1.0%	2.0%	Water ISO 105 E01	Chlorinated Pool Water AATCC 162:2002	Hydrogen Peroxide	Perspiration ISO 105 E04 Acid / Alkali
Yellow EGB		100	L	L	60	S	S	S	S	Moderate	4-5	4 3-4	3	3-4	4	4-5	2-3	4	5 4-5
Ultra Yellow EGB		80	L	H	60	S	S	S	S	Moderate	4-5	4 4	3-4	4	4	4-5	3-4	4	4-5 4-5
Orange EGB		100	H	H	60	S	S	S	S	Moderate	4	4 3-4	3	3-4	4	3-4	2-3	3-4	4 4
Ultra Orange EGB		100	H	H	60	S	S	S	S	Moderate	4	4 3-4	3	3-4	4	3-4	2-3	3-4	4 4
Scarlet EGB		100	L	H	60	S	S	S	S	Good	4-5	4-5 3	3	3-4	4	4-5	2-3	4	4 4-5
Red EGB		120	M	H	60	S	S	S	S	Moderate	4	4-5 4	3	3	3-4	4	4	3-4	4-5 4-5
Deep Red EGB		100	H	H	60	S	S	S	S	Moderate	4	4 3-4	-	3	3-4	4	-	3-4	3-4 4
Ultra Red EGB		120	M	H	60	S	S	S	S	Moderate	4	4-5 4	3	3	3-4	4	4	3-4	4-5 4-5
Ultra Carmine EGB		100	L	H	60	S	S	S	S	Good	4-5	4-5 3	3	3-4	4	4-5	2-3	4	4 4-5
Blue EGB		100	L	H	60	S	S	S	S	Good	4	4 3-4	3	3-4	4	4-5	3-4	4-5	4-5 4-5
Navy Blue EGB		150	L	H	60	S	S	S	S	Good	4-5	4-5 3	3	3-4	4	4-5	2-3	4	4 4-5
Grey EGB		80	L	H	60	S	S	S	S	Moderate	4-5	4 4	3-4	4	4	4-5	3-4	4	4-5 4-5
Deep Black N-150		150	L	H	60	S	S	S	S	Good	4-5	4-5 3	3	3-4	4	4-5	2-3	4	4 4-5
Black EGBNN		150	L	H	60	S	S	S	S	Good	4-5	4-5 3	3	3-4	4	4-5	2-3	4	4 4-5

RR DYES



Yellow RR		120	M	M	60	S	S	S	S	Good	4	4-5 4	4	4.5	4.5	4-5	3.5	4	4-5 4-5
Red RR		80	M	H	60	S	S	S	S	Poor	3-4	4-5 3	3.5	3.5	4	3-4	3.5	4	4 4
BLUE RR		120	H	H	60	HS	S	S	S	Good	4	4-5 4	3	3.5	4	4	4	4	4-5 4-5

H - High | **M** - Medium | **L** - Low | **HS** - High Suitable | **S** - Suitable | **LS** - Low Suitable | **NS** - Not Suitable

