




 EQUINATIVE SW DYES SERIES	Shade 2.0% o.w.f.	Solubility in gpl at 300C	Affinity	Reactivity	Fixation Temperature	Process Suitability				Dischargeability	Other Fastness		Light Fastness AATCC 16E			Post Fastness Properties			
						Exhaust	Cold Pad Batch	Printing	Continuous		Washing Fastness ISO 105 C04	Rubbing ISO 105/X12 Dry / Wet	0.1%	1.0%	2.0%	Water ISO 105 E01	Chlorinated Pool Water AATCC 162:2002	Hydrogen Peroxide	Perspiration ISO 105 E04 Acid / Alkali
Lemon Yellow S3G		80	H	L	60	LS	S	S	NS	Moderate	4-5	4-5 4-5	4	4	4	4-5	3	4-5	4-5 4-5
Yellow S3R		150	H	L	60	HS	S	S	S	Poor	4	4-5 3-4	3	4	4	4	4-5	4-5	4 4
Orange W3R		150	H	M	60	HS	HS	S	S	Good	4-5	4-5 4	3	3-4	4	4-5	3-4	5	4-5 4-5
Deep Orange S4R		80	H	M	60	S	NS	LS	LS	Moderate	4-5	4 3-4	2-3	3	3-4	3-4	3-4	4	4 4
Red S2B		200	H	M	60	HS	HS	S	S	Moderate	4-5	4 4	3	3-4	4	4-5	4	4	4-5 4
Deep Red SB		200	H	M	60	HS	HS	S	S	Moderate	4	4 4	3	3-4	3-4	4	4	4	4-5 4
Cherry Red SD		100	H	M	60	HS	HS	S	S	Good	4	4-5 3-4	3	3-4	3-4	4	3	3-4	4-5 4-5
Ruby S3B		150	M	M	60	HS	HS	S	S	Poor	4-5	4 4	3	3-4	3-4	4-5	4	3	4-5 4-5
DK Blue SGL		150	H	L	60	HS	LS	S	LS	Moderate	4-5	4-5 4	3-4	4	4	4-5	4	3	4-5 4-5
Navy SGI		150	H	H	60	HS	HS	S	S	Good	4	4-5 3-4	3	3-4	3-4	4	5	4	5 5
Deep Night SR		250	H	M	60	HS	HS	S	S	Good	4	4 3-4	2-3	3	3	4	2	4	4-5 4-5
Super Black R		200	H	H	60	HS	HS	S	S	Good	4	4-5 3-4	-	3	3-4	4	3	4	4-5 4-5
Super Black G		200	H	H	60	HS	HS	S	S	Good	4	4-5 3-4	-	3	3-4	4	3	4	4-5 4-5
Black NN		200	H	H	60	HS	HS	S	S	Good	4	4-5 3-4	-	3	3-4	4	3	4	4-5 4-5
Black WF		200	H	H	60	HS	HS	S	S	Good	4	4-5 3-4	-	3	3-4	4	3	4	4-5 4-5

H - High | **M** - Medium | **L** - Low | **HS** - High Suitable | **S** - Suitable | **LS** - Low Suitable | **NS** - Not Suitable

